

Polyester in Sheets - GDZC050

Facestock:

A transparent and clear Polyester.

Laminate Data:

| Facestock | | Liner | | Total ±10% | |
|-----------------|-------------|-------|-----|-------------|--------------|
| Type | Caliper (μ) | Type | gsm | Caliper (μ) | Weight (gsm) |
| Polyester White | 50 | cck | 135 | 200 | 226 |
| Polyester Clear | 50 | cck | 135 | 200 | 226 |

Description:

Filmic facestock permanent acrylic adhesive with high moistures resistance.

Temperature:

Min' application: > 0°C

Service: -20°C/100°C

Performance and Use:

This adhesive has been specially developed for use with clear filmic face materials, providing a strong bond to polar, and non-polar, substrates alike.

It may be used where good transparency is required in combination with clear films.

| | | |
|---------------------|------------|------------|
| Initial Tack | 10N / 25mm | FTM9 glass |
| Peel Adhesion 180°C | 11N / 25mm | FTM1 St.St |

Printing methods:

Suitable for various printing methods, including: Laser printing, Thermal transfer, Letterpress, Offset, Flexo and silk screen printing.

Shelf life:

2 years under storage conditions as defined by FINAT.

Temperature: 20-25°C

Humidity: 40-50% RH

All figures to be considered as typical values.

E-mail: jolybar@jolybar.com

Internet Sites: www.jolybar.com | www.ecojo-nature-packs.com | www.jolycake.com