



ZHEJIANG GANGLONG NEW MATERIAL CO., LTD.

MAQIAO WARP KNITTING SCIENCE & TECHNOLOGY INDUSTRIAL ZONE

HAINING ZHEJIANG CHINA, 314419

TECHNICAL DATA GLP005-B

COATED FRONTLIT (G/M)

Item	Unit	Value	Test Method
Base Fabric	Denier (High tenacity yarn) 100%PES	1000DX1000D	DIN EN ISO2060
Construction	Weaving /inch	18x18	DIN60001
Weight of fabric	Gsm/m2	157±5	DIN53352 BS3424 Method5B
Weight of PVC	Gsm/m2	293±5	DIN53352 BS3424 Method5B
Total weight	Gsm/m2	450±10	DIN53352 BS3424 Method5A
Thickness	mm	0.37±0.02	DIN EN ISO 2286-3
Width	cm	Up to 510	/
Breaking Strength	N/5cm	Warp	2200
		Weft	1900
Tearing Strength	N	Warp	300
		Weft	250
Adhesion	N/5CM	80	DIN53357 BS3425 Method9B
Temperature Resistance	°C	-20~70	DIN53357 BS3425 Method10
Lacquering	NONE		
Flammability	If the client need ,We can reach: B1, B2, NFPA701, DIN75200 etc.		
LOW CADMIUM & HEAVY METALS	If the client need ,We can reach: EN71-3		
Conclusions and Announcements	<p>Declaration by GLP: Please choose GLP products suitably according to relative provisions or industrial standards. GLP bears the responsibility for the specified technical and performance data on this page only. GLP is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)</p> <p>Remarks : ‘G’represents Glossy surface, ‘M’ represents Matte surface, Glossy or Matte could be made as requirements</p>		