



Model GmbH
Wildeck Str. 12
D-99837 Berka/Werra
T +49 (0) 36922 80 200
F + 49 (0) 36922 80 260
modelgroup.de

Data sheet 160 e KGsww

An JOLYBAR
E-Mail
Datum: 26.04.2017

Quality : 160 e KGsww

Paper composition :

Outside - 185g Kraftliner white coated
e-Corrugation - 100g Fluting Medium
Inside - 135g Kraftliner white

Technische Werte :

- Edge Crush Test - ECT (kN/m) : 5,4 +/-5%
- Bursting Strength - BST (kPa) : 1300 +/-7,5%
- Puncture Energy Test - PET (J) : 3,6 +/-6%
- Thickness (mm) : 1,54 +/-5%

Commercial variations in color, weight and thickness of the processed papers are possible.

K. Schäfer
Model GmbH