



Model GmbH  
Wildecker Str. 12  
D-99837 Berka/Werra  
T +49 (0) 36922 80 200  
F + 49 (0) 36922 80 260  
modelgroup.de

## Data sheet 240 ee KGsww

An JOLYBAR  
E-Mail  
Datum: 26.04.2017

**Quality : 240 ee KGsww**

**Paper composition :**

Outside	- 185g Kraftliner white coated
e-Corrugation	- 100g Fluting Medium
Intermediate ply	- 100g Fluting Medium
e-Corrugation	- 100g Fluting Medium
Inside	- 135g Kraftliner white

**Technische Werte :**

- Edge Crush Test - ECT (kN/m)	: 9,4	+/-5%
- Bursting Strength - BST (kPa)	: 1450	+/-7,5%
- Puncture Energy Test - PET (J)	: 7,0	+/-6%
- Thickness (mm)	: 2,80	+/-5%

**Commercial variations in color, weight and thickness of the processed papers are possible.**

**K. Schäfer**  
**Model GmbH**