



PREMIUM BACKLIT FABRIC

PRODUCT: ST-103

FEATURES / APPLICATIONS:

- 100%Polyester woven, Semi-glossy finish.
- Super tight base structure for good opacity.
- Combined with dye-sub direct, dye-sub transfer and latex inks



MATERIAL DETAILS

PROPERTIES	TEST METHOD	METRIC	IMPERIAL
Total Weight	DIN EN ISO 2286-2	270g/sq.m	8 oz/sq.yd.
Base Fabric	DIN 60001	Polyester	Polyester
Yarn Dtex	DIN EN ISO 2060	165x165 dtex	150x150 denier
Weave Method	N/A	Woven	
White Point (CIE/D65)	CIE86/ASTME313-00(D65/10,SCI)	≥126	
Shrinkage	N/A	≤2% (190°C , 1min)	
Flame Resistance	/	DIN 4102-1-B1	
Recommend fixation temperature	N/A	190°C-210°C , 1-2min	
Transfer temperature	N/A	190°C-210°C , 1-2min	
Yellowing temperature	SUPRKC REX-C400	230°C	
Width	N/A	Max 320cm	126"
Standard Length	N/A	50m	55yd

INK PRINTABILITY

Solvent	Eco Solvent	UV	Latex
		<input type="checkbox"/>	<input type="checkbox"/>
Screen Printing	Dye Transfer	Dye Direct	
	<input type="checkbox"/>	<input type="checkbox"/>	

NOTE: All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty

**Soyang Technologies Co., Ltd
(Soyang Headquarters)**

West 19th FL, Yongtong Information plaza, No. 141 Huancheng Bei Road, Hangzhou City, Zhejiang PR., China.

www.soyang.net

P. 0086-571-28918690

F. 0086-571-28918695

Soyang Haining Factory

No.36 Jinniu Road,Jianshan District,Haining City, Zhejiang PR,China.

Soyang Hangzhou Factory

No,1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China

Soyang Europe Ltd

Calder House Metcalf Drive
Altham Industrial estate

www.soyang.co.uk

P. 0044 (0) 161 765 3400

F. 0044 (0) 1282 772982