



Model GmbH
Wildecker Str. 12
D-99837 Berka/Werra
T +49 (0) 36922 80 200
F + 49 (0) 36922 80 260
modelgroup.de

Data sheet 240 eb KGsww

An JOLYBAR
E-Mail
Datum: 26.04.2017

Quality : 240 eb KGsww

Paper composition :

Outside	- 185g Kraftliner white coated
e-Corrugation	- 100g Fluting Medium
Intermediate ply	- 100g Fluting Medium
b-Corrugation	- 100g Fluting Medium
Inside	- 135g Kraftliner white

Technische Werte :

- Edge Crush Test - ECT (kN/m)	: 9,4	+/-5%
- Bursting Strength - BST (kPa)	: 1450	+/-7,5%
- Puncture Energy Test - PET (J)	: 7,3	+/-6%
- Thickness (mm)	: 4,05	+/-5%

Commercial variations in color, weight and thickness of the processed papers are possible.

K. Schäfer
Model GmbH