

**GDZC050**

Polyester in Sheets, P25

**Facestock:** A clear Polyester.

**Laminate Data:**

Facestock		Liner		Total (±10%)	
Type	Caliper (μ)	Type	gsm	Caliper (μ)	Weight (gsm)
Polyester Clear	50	CCK	135	200	226

**Adhesive – P25:**

**Description:** Filmic feacstock acrylic adhesive with high moistures resistance.

**Temperature:** Min' application: >0°C

Service: -20°C/100°C

**Performance & Use**

This adhesive has been specially developed for use with clear filmic face materials providing a strong bond to polar and non-polar substrates alike.

It may be used where good transparency is required in combination with clear films.

Initial Tack	10 N/25mm	FTM9 glass
Peel Adhesion 180°	11 N/25mm	FTM1 St.St

**Printing Methods**

Suitable for various printing methods, including: Laser printing, Thermal transfer, Letterpress, Offset, Flexo and silk screen printing.

**Shelf life:** 2 years under storage conditions as defined by FINAT.

**Temperature:** 20-25°C

**Humidity:** 40-50%RH

All figures to be considered as typical values

This data is intended to be a guide to the values which may generally be expected. since the final use of the product is outside our control, we strongly advise prior testing of its suitability for a particular purpose.

