GDZG050

Polyester in Sheets, P25

Facestock: A white gloss Polyester.

Laminate Data:

Facestock		Liner		Total (±10%)	
Type	**Caliper (µ)**	**Type**	**gsm**	**Caliper (µ)**	**Weight (gsm)**
Polyester White	50	CCK	135	200	226

Adhesive – P25:

Description: Filmic feacstock acrylic adhesive with high moistures resistance.

Temperature: Min' application: >0ºc Service: -20ºc/100ºc

Performance & Use

This adhesive has been specially developed for use with clear filmic face materials providing a strong bond to polar and non-polar substrates alike.

It may be used where good transparency is required in combination with clear films.

Initial Tack	10 N/25mm	FTM9 glass
Peel Adhesion 180º	11 N/25mm	FTM1 St.St

Printing Methods

Suitable for various printing methods, including: Laser printing, Thermal transfer, Letterpress, Offset, Flexo and silk screen printing.

Shelf life: 2 years under storage conditions as defined by FINAT.

Temperature: 20-25ºc **Humidity:** 40-50%RH

All figures to be considered as typical values

This data is intended to be a guide to the values which may generally be expected. since the final use of the product is outside our control, we strongly advise prior testing of its suitability for a particular purpose.

www.jolybar.com
www.jolycake.com
E-mail: jolybar@jolybar.com
2 Hadas St. Industrial Zone Alon Tavor
P.O. Box 15157, Zip Code 1811001, ISRAEL
Tel: +972-4-6407333