

GDZG200

Polyester in Sheets, P25

Facestock: A white gloss with slit Polyester.

Laminate Data:

Facestock		Liner		Total ($\pm 10\%$)	
Type	Caliper (μ)	Type	gsm	Caliper (μ)	Weight (gsm)
Polyester White	50	CCK	135	200	226

Adhesive – P25:

Description: Filmic facestock acrylic adhesive with high moistures resistance.

Temperature: Min' application: $>0^{\circ}\text{c}$

Service: $-20^{\circ}\text{c}/100^{\circ}\text{c}$

Performance & Use

This adhesive has been specially developed for use with clear filmic face materials providing a strong bond to polar and non-polar substrates alike.

It may be used where good transparency is required in combination with clear films.

Initial Tack 10 N/25mm FTM9 glass

Peel Adhesion 180° 11 N/25mm FTM1 St.St

Printing Methods

Suitable for various printing methods, including: Laser printing, Thermal transfer, Letterpress, Offset, Flexo and silk screen printing.

Shelf life: 2 years under storage conditions as defined by FINAT.

Temperature: 20-25°c

Humidity: 40-50%RH

All figures to be considered as typical values

This data is intended to be a guide to the values which may generally be expected. since the final use of the product is outside our control, we strongly advise prior testing of its suitability for a particular purpose.

