

## GDZM050

Polyester in Sheets, P25

**Facestock:** A white matt Polyester.

### Laminate Data:

Facestock		Liner		Total ( $\pm 10\%$ )	
Type	Caliper ( $\mu$ )	Type	gsm	Caliper ( $\mu$ )	Weight (gsm)
Polyester White	50	CCK	135	200	226

### Adhesive – P25:

**Description:** Filmic facestock acrylic adhesive with high moisture resistance.

**Temperature:** Min' application:  $>0^{\circ}\text{C}$

Service:  $-20^{\circ}\text{C}/100^{\circ}\text{C}$

### Performance & Use

This adhesive has been specially developed for use with clear filmic face materials providing a strong bond to polar and non-polar substrates alike.

It may be used where good transparency is required in combination with clear films.

Initial Tack                                      10 N/25mm                                      FTM9 glass

Peel Adhesion 180°                              11 N/25mm                                      FTM1 St.St

### Printing Methods

Suitable for various printing methods, including: Laser printing, Thermal transfer, Letterpress, Offset, Flexo and silk screen printing.

**Shelf life:** 2 years under storage conditions as defined by FINAT.

**Temperature:** 20-25°C

**Humidity:** 40-50%RH

All figures to be considered as typical values

This data is intended to be a guide to the values which may generally be expected. since the final use of the product is outside our control, we strongly advise prior testing of its suitability for a particular purpose.

